



# Bitu Cutback\*



Protect Environment

Always Think

Green



## Solvent base bitumen prime / tack coat

### Uses

The major use of cutback is to protect the underlying layers from wet weather by providing a temporary waterproofing layer, Additional benefits of cutback is to stabilizing or binding the surface fines together and promoting bond to the HMA layer. Cutback increased the bond strength at the interface between a compacted base and asphalt layer.

### Advantages

- Penetrate into the absorbent surface and bind the granular material together.
- Harden or toughen the surface
- Partially waterproof the treated areas to make them resistant to water erosion
- Does not affect the base bitumen properties
- Provide adhesion between the base and the next course
- Provide protection from wind, water, and traffic erosion

### Compliance to ASTM Standards

RC Type: ASTM D2028-76, AASHTO M-81  
MC Type: ASTM D2027-76, AASHTO M-82

### Description

**Bitu Cutback\*** is combination of asphalt and petroleum solvent of a Kerosene type, **Bitu Cutback\*** is available in two grades, **RC (Rapid Cure) RC-70 RC-250, RC-800 & MC (Medium Cure) MC-70, MC-250, MC800**

### Surface Preparation

Bitu Cutback\* can be applied in some situations without any preparation. However, the beneficial effects will be reduced by an extremely dry material, the presence of highly compacted areas, potholes, and high spots. To optimize the performance of Bitu Cutback\* the following steps should be employed:

### Grading

Using a road grader, an angled dozer, or shovels and rakes, remove, mix and replace the top 50 to 150 mm (2 to 6 in.) of material.

Insure that the surface is free from local high spots and potholes, and that the material is evenly mixed and distributed to avoid segregated pockets of coarse or fine aggregate.

### Watering

Water should be applied 2 to 12 hours before priming; the material at the time of priming surface should be dry.

### Application

**Bitu Cutback\*** is sprayed at about 0.65 – 1.75 Kg / m<sup>2</sup> as prime coat & 0.20 – 0.65 Kg. / m<sup>2</sup> as tack coat, Do a test area to check the level of penetration first. Adjust spray temperature if necessary. Spray using a standard sprayer that is properly calibrated.

Allow penetrating and drying. Usually traffic should not be allowed on to this for 24 hours.

### Technical support

Pakistan Bitumen Company provides a technical advisory service for on-site assistance and advice on selection of Cutback grade, as per site conditions.

### Precaution / Limitation


**Bitu Cutback\*** shall not be applied when the ambient temperature is below - 10° C, or when rain is imminent.

**Bitu Cutback\*** may be harmful to growing plants, since like any other oil, it seals pores and interferes with intake of carbon dioxide. Reasonable care should be taken to pre-vent overspray on crops. Also, since the product is black, reasonable care should be taken to prevent spraying on buildings, fences, and other areas where dark stains are undesirable.

Avoid skin and eye contact, in case of contact, use suitable solvent and seek medical advice, use the appropriate means if self protection, it must not be disposed to surface and in still water.

Traffic should be kept off the treated surfaces until the product has penetrated and the surface is no longer tacky. There should be no pickup of the treated materials on shoes or tires.

If puddles develop in low spots, clean sand or soil should be applied to blot them.



**Bitu Cutback\*** is in the hazardous classifications of current regulations. It should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with suitable solvent. In case of contact with eyes rinse immediately with plenty of water and seek medical advice.

#### Properties of RC (Rapid Cure) Cutback

Grade	RC-70		RC-250		RC-800	
	Min.	Max.	Min.	Max.	Min.	Max.
Limits						
Water percent	-	0.2	-	0.2	-	0.2
Flash point (Tag. Open cup) °C	-	-	27	-	27	-
Kinematic viscosity at 60 °C	70	140	250	500	800	1600
Saybolt Furol Viscosity at 50 °C Sec.	60	120				
Saybolt Furol Viscosity at 60 °C Sec.			125	250		
Saybolt Furol Viscosity at 82.2 °C Sec.					700	1500

#### Properties of MC (Medium Cure) Cutback

Grade	MC-70		RC-250		RC-800	
	Min.	Max.	Min.	Max.	Min.	Max.
Limits						
Water percent	-	0.2	-	0.2	-	0.2
Flash point (Tag. Open cup) °C	38	-	66	-	66	-
Kinematic viscosity at 60 °C	70	140	250	500	800	1600
Saybolt Furol Viscosity at 50 °C Sec.	60	120				
Saybolt Furol Viscosity at 60 °C Sec.			125	250		
Saybolt Furol Viscosity at 82.2 °C Sec.					700	1500

#### Storage

**Bitu Cutback\*** has a shelf life of 12 months provided the temperature is kept within the range of 5°C to 40°C with tight lid closed container. Should the temperature of the product fall outside this range then contact your local office for advice.

**Fire:** **Bitu Cutback\*** is solvent base and flammable.

**Freezing point:** Approximate – 20 °C

#### Estimating – Packaging

**Bitu Cutback\*** is available in 218 Kg. Drum and bulk supply.

#### Pre-Heating

Need to be heated when spray.

RC-70 & RC-250 = 55 – 80 °C

RC-800 = 75 – 100 °C

MC-70 & MC-250 = 55 – 80 °C

MC-800 = 75 – 100 °C

#### REGIONAL SALES OFFICES IN PAKISTAN:

### Pakistan Bitumen Company Subsidiary of Fospak (Pvt) Ltd.

#### Head Office

702, Business Avenue,  
Block-6, PECHS.  
Shahra-e-Faisal,  
Karachi, Pakistan  
Tel # +92-21-34528477,34529859  
Fax # +92-21-34522436  
Email [info.khi@fospak.com.pk](mailto:info.khi@fospak.com.pk)

#### Lahore Sales Office

2<sup>nd</sup> Floor Sarwar Shaheed Plaza,  
Cavalry Ground,  
Main Boulevard,  
Lahore Cantt, Lahore.  
Tel # +92-42-36675773  
Fax # +92-42-36675838  
Email [info.lhr@fospak.com.pk](mailto:info.lhr@fospak.com.pk)

#### Rawalpindi Sales Office

1<sup>st</sup> Floor, Al-Harain Plaza,  
Main Murree Road,  
Rawalpindi  
Tel # +92-51-9290592  
Fax # +92-51-9290590  
Email [info.isb@fospak.com.pk](mailto:info.isb@fospak.com.pk)

#### Important note

PBC products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst PBC endeavours to ensure that the technical information on this data sheet is correct at the time of printing, it is the customer's responsibility to satisfy himself, by checking with the company that this information is still current at the time of use, that the product is suitable for the intended application, and that the actual conditions of use are in accordance with those recommended. Because PBC has no control over the conditions of use of its products, all recommendations or suggestions regarding the use of these products are made without guarantee.

