

Expanbond* PVA



CONSTRUCTION CHEMISTRY

Multipurpose PVA adhesive, sealer and cement admixture

Uses

As a multipurpose adhesive: plaster bonding agent: primer, and integral bonding agent for concrete and granolithic floor repairs: repair of natural and reconstructed stone: bonding agent for tiles: bonding granolithic toppings to sub-concrete, dust proofing floor screeds and friable concrete flooring: primer for overcoating bitumen with oil based paints.

Advantages

- Single component liquid, gauged as required
- Bonds most common construction materials
- Improves the durability of mortars and renders
- Excellent as a dustproofer and sealer
- Easily applied by brush roller or spray
- Contains no chloride admixtures
- Versatile and economical

Description

Expanbond* PVA multipurpose adhesive is supplied as a ready to use white liquid based on a polymerized resin

Properties

Appearance : White viscous liquid

Specific gravity : Typically 1.0 @ 20°C

Chloride content : Nil to (BS 5075)

Compatibility with : Can be used with all types cements of Portland cement

Expanchem Fospak Technical Service Department should be consulted prior to using Expanbond* PVA in combination with admixtures.

Specification clauses

Polymer bonding aid and mortar additive

The polymer bonding aid and mortar additive shall be Expanbond* PVA, a single component polymerized resin emulsion.

Instructions for use

Preparation

Saw cut the extremities of any repair locations to a depth of at least 10 mm to avoid feather-edging and to provide

Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae. Where breaking out is not required, roughen the surface and remove any laitance by light scabbling, grit-blasting or other suitable mechanical means.

Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should then be assessed by a pull-off-test.

Surface sealing

Porous surfaces should be sealed with a solution of 1 part Expanbond* PVA to 15 parts clean water. Where surface porosity is extremely high it may be necessary to increase the concentration to 1 part Expanbond* PVA to 10 parts water.

Breeze, foam, slag and other lightweight building blocks are exceptionally absorbent and will require pre-soaking

Application

Please note: Expanbond* PVA should not be used as a bonding agent in continuously wet areas. In such conditions Expanbond SBR is recommended.

Expanbond* PVA may be applied by brush or roller as indicated in the following specific applications:

1. As a General adhesive

Bonds asbestos, bricks, carpet, china, concrete, cork, earthenware, glass, laminated plastic, leather, linoleum, plasterboards, polystyrene, renders, roofing felt, stone, textiles, tiles and wood.

After surface preparation, apply a thin film of Expanbond* PVA over both faces and allow to become tacky (20 to 30 minutes depending upon temperature). Bring the surfaces firmly together, position as required, wipe of any excess and allow to set for 24 hours. Do not clamp tightly as the Expanbond* PVA may be squeezed out.

NB. Expanbond* PVA will not bond polythene, PVC or rubber.



CONSTRUCTION CHEMISTRY

2. As a plaster bonding agent

Reduces hacking and keying and will provide an adhesive or mechanical key to receive plaster or render coats of gypsum, lightweight gypsum, or anhydrous plasters, plastering onto tiles.

For gypsum, lightweight gypsum and anhydrous plasters seal as required and prime with a solution of 1 part Expanbond* PVA to one part water and allow to become tacky. Then plaster straight onto the tacky Expanbond* PVA as per the normal method.

For heavier renderings and cementitious toppings seal and prime as above and then prepare a key coat by mixing 1 part Portland cement, 1 part clean washed sharp sand, gauged to a stiff consistency with 1 part Expanbond* PVA to 3 parts clean water. Apply this to the tacky priming coat to an average thickness of 1-2 mm and stipple with a stiff brush, or otherwise roughen the surface to provide a good mechanical key. Allow to harden and dry thoroughly. Test for adhesion prior to applying render.

For plastering onto glazed tiles, to ensure a satisfactory bond a mechanical key should be provided by light peck hammering prior to sealing, priming and plastering as above.

3. For repairs to concrete

Prepare and seal the surface as required, apply a priming coat of 1 part Expanbond* PVA to 1 part water and allow to become tacky. Using the same sand or fine aggregate as in the concrete to be repaired, prepare a stiff cement/sand mix in the proportions 1:2 (or leaner) gauged with 1 part Expanbond* PVA to 3 parts clean water. Compact firmly and level out with minimum trowelling.

4. Repairs to Natural or Reconstructed Stone

Prepare and seal the surface as required and apply the priming coat as above. Prepare a stiff mix comprising of Portland cement with original aggregate in as lean a mix as possible 1:6 (or leaner) consistent with the strength requirements gauged with 1 part Expanbond* PVA to 3 parts clean water. Compact firmly and level with the minimum of trowelling.

Note: Resurfacing does not normally call for high strengths. Colours can be matched by adding suitable pigments to the mix. Where high strengths are required the Expanchem Fospak Technical Department should be consulted for advice on alternative materials.

5. For repairs to concrete and granolithic floors

Prepare and seal the surface as required. Apply the priming coat of 1 part Expanbond* PVA to 1 part water, brush well into all crevices and allow to become tacky. The priming coat must never be allowed to dry, if it does re-prime and proceed only when tacky.

Prepare a mix of 1 part of Portland cement to 2.5 parts of clean washed sharp sand, gauged to a stiff consistency with 1 part Expanbond* PVA to 3 parts clean water. Then proceed as per the particular application as detailed below:

Repairing Cracks and Holes in Cementitious Floors: Place the mix onto the tacky prime coat, compact firmly and level out to a smooth finish with minimum trowelling. Deep holes and cracks should be filled with conventional concrete onto the tacky priming coat to within 6mm of the surface and "topped" off to above specification whilst the ordinary concrete fill is still green.

Resurfacing of worn concrete and granolithic floors: Place the mix onto the tacky sealing coat and trowel in to the surface using existing exposed aggregate as level thus replacing mortar lost by wear. Treat deep indentations or holes as per above.

Leveling of worn stair treads: Place the mix onto the tacky priming coat, compact firmly and level out to a smooth finish with the minimum of trowelling. To impact a nonslip finish to the stair tread, a piece of hessian should be placed onto the newly filled area soon after trowelling and lightly tamped to leave an impression of the hessian.

6. As a bonding agent for tiles

Wood, block, cork, lino and acoustical tiles: Use Expanbond* PVA as a general adhesive. If the surface is uneven, the adhesive should be filled as described below under "Polystyrene Tiles."

Ceramic, concrete, quarry, clay and terrazzo tiles: Seal with a solution of 1 part Expanbond* PVA to 5 parts water. Brush well into the surface and allow to dry.

Before bedding tiles in sand and cement give the floor and the base of the tiles a further coat of 3 parts Expanbond* PVA to 1 part water. Whilst this is still wet or tacky apply the sand and cement bedding to the base and bed the tiles.

Polystyrene tiles, plaster board and acoustic board: Prepare and seal the surface as required, then using a suitable filler such as plaster, cement, fine sand or sawdust, make a paste with a solution of 1 part Expanbond* PVA to 1 part water. Apply this mixture as an adhesive coat to the tiles and surface to be bonded.



CONSTRUCTION CHEMISTRY

7. For bonding granolithic toppings to sub-concrete

Prepare the surface and apply a priming coat of 1 part Expanbond* PVA to 1 part water, brush well into all crevices and allow to become tacky. The priming coat must never be allowed to dry, if it does then the surface must be reprimed.

Prepare a key coat consisting of 1 part Portland cement to 1 part clean sharp sand gauged to a stiff consistency with a solution of 1 part Expanbond* PVA to 3 parts water. Spread over the area whilst the priming coat is still tacky to an average depth of 6 mm then stipple with a stiff brush to form a mechanical key i.e: as rough a surface as possible. Allow to harden thoroughly and check for adhesion prior to laying the granolithic topping.

8. As a primer for overcoating bitumen with oil based paints

Coat the bitumen with a solution of 1 part Expanbond* PVA to 1 part water as an anti-bleed priming coat suitable for most oil- based paints.

High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade and cool water used for mixing.

Curing

Expanbond* PVA mortars, toppings and renders are cement based. In common with all cementitious materials, they must be cured immediately after finishing in accordance with good concrete practice.

The use of Concure* curing membranes is recommended. In harsh drying conditions, supplementary curing with damp hessian or polythene sheeting is strongly

Cleaning

Expanbond* PVA should be removed from tools, equipment and mixers with clean water immediately after use. Spillages should be absorbed with clean sand or sawdust and disposed of in accordance with local Health and Safety regulations.

Limitations

Expanbond* PVA mortars, toppings and renders should not be applied when the temperature is below 5°C and falling. Neither should they be exposed to moving water during application. Exposure to heavy rainfall prior to the final set may result in surface scour. If any doubts arise concerning temperature or substrate conditions, consult the local Expanchem Fospak office.

Technical support

Expanchem Fospak offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Estimating

Supply

Expanbond* PVA : 30 and 210 liter drums

Coverage

Sealer coat : 75m² diluted 1 to 15
50m² diluted 1 to 10
25m² diluted 1 to 5

Primer coat : 5m² diluted 1 to 1

Key coat : 3m² diluted 1 to 3

Note: The coverage figures for Expanbond* PVA are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

Storage

Shelf life

All products have a shelf life of 6 months if kept in a dry store in the original, unopened bags or packs.

Storage conditions

Store in dry conditions in the original packing. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced. Expanbond* PVA should be protected from frost.

Precautions

Health and safety

Cementitious mortars and slurries modified with Expanbond PVA contain cement powders which, when mixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes.

Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water.



CONSTRUCTION CHEMISTRY

Additional Information

Expanbond* PVA should not come in contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapors. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. If swallowed, seek medical attention immediately -do not induce vomiting.

Fire

Expanbond* PVA is non-flammable.

Expanchem Fospak manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialized flooring materials

Expanchem Fospak additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Expanchem Fospak's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Expanchem Fospak office.

* Denotes the trademark registered

REGIONAL SALES OFFICES IN PAKISTAN:

Fospak (Pvt) Ltd.

Head Office

702, Business Avenue,
Block-6, PECHS., Shahra-e-Faisal,
Karachi, Pakistan.

Tel # +92-21-34528477, 34529859

Fax # +92-21-34522436

Email : info.khi@fospak.com.pk

Lahore Sales Office

2nd Floor Sarwar Shaheed Plaza,
Cavalry Ground,
Main Boulevard, Lahore Cantt,
Lahore, Pakistan.

Tel # +92-42-36675773

Fax # +92-42-36675838

Email : info.lhr@fospak.com.pk

Rawalpindi Sales Office

1st Floor,
Al-Harmain Plaza,
Main Murree Road,
Rawalpindi, Pakistan.

Tel # +92-51-9290592

Fax # +92-51-9290590

Email : info.isb@fospak.com.pk

Important note

Expanchem Fospak products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Expanchem Fospak endeavours to ensure that the technical information on this data sheet is correct at the time of printing, it is the customer's responsibility to satisfy himself, by checking with the company that this information is still current at the time of use, that the product is suitable for the intended application, and that the actual conditions of use are in accordance with those recommended. Because Expanchem Fospak has no control over the conditions of use of its products, all recommendations or suggestions regarding the use of these products are made without guarantee.

www.fospak.com