

Expanbond* SBR



CONSTRUCTION CHEMISTRY

Polymer bonding aid and additive for mortar, screeds and renders

Uses

For improving the physical properties of cementitious mixes. Typical uses include, but are not limited to, the following:

- Bonding concrete repair mortars
- Floor toppings and screeds
- Waterproof renders and cementitious slurries
- Bonding agent for slip bricks, ceramic tiles, etc.

Advantages

- Single component liquid can be easily gauged as required
- Improves cohesion and workability
- Improves mortars to provide waterproof repairs, renders and toppings which are highly resistant to freeze/thaw cycling
- Improved tensile and flexural properties allow thin applications
- Excellent bond to concrete, masonry, stonework, plaster and block-board.
- Contains no chloride admixtures

Specification

Polymer bonding aid and mortar additive

The polymer bonding aid and site-batched mortar shall be modified by the use of Expanbond* SBR, a single component styrene butadiene rubber emulsion.

Description

Expanbond* SBR is a modified styrene butadiene rubber emulsion which is supplied as a ready to use white liquid. It is designed to improve the quality of site-batched cementitious mortars and slurries. Being resistant to hydrolysis, it is ideal for internal and external applications in conjunction with cement.

Technical Support

Expanchem Fospak offers a comprehensive range of high performance, high quality flooring, jointing and repair products for both new and existing floor surfaces. In addition, the company offers a technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in location all over the world.

Properties

The results listed below were achieved by assessing the mechanical properties of a 3:1 sand: cement mortar containing Expanbond* SBR in the proportions 10 liters per 50 kg cement against a 3:1 sand: cement control mortar. The test methods used were in full accordance with BS 6319 at 28 days-air cured.

Test method	Typical result	Control
Compressive strength (BS 6319, Pt2)	: 35 N/mm ²	28 N/mm ²
Tensile strength (ASTM C-190)	: 5.5 N/mm ²	2.7 N/mm ²
Flexural strength (BS 6319, Pt3)	: 11.5 N/mm ²	7.9 N/mm ²
Slant shear bond (BS 6319, Pt4)	: 38 N/mm ²	2.6 N/mm ²

Chemical resistance

Cementitious materials have limited chemical resistance. The addition of Expanbond* SBR to cement mortar reduces permeability and therefore helps reduce the rate of attack by aggressive chemicals, acid gases and water.

Design criteria

The application parameters for mortars modified by the use of Expanbond* SBR will differ depending on the actual mix design used, but should always be subject to a minimum applied thickness of 6 mm.

Expanbond* SBR-modified mortars can generally be applied in sections of up to 40 mm thickness in horizontal location and 15 mm in vertical locations, without the use of formwork.

In overhead locations the thickness achievable without the use of formwork is largely dependent on the profile of the substrate. Consult the local Expanchem Fospak office for further information.

Instructions for use

Preparation

Form the extremities of the application area to a depth of at least 10 mm to avoid feather-edging and to provide a square edge. Ensure a minimum depth of 6 mm is observed in the remaining area, up to the previously formed edge.



CONSTRUCTION CHEMISTRY

Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae. Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser.

Where breaking out is not required, roughen the surface and remove any laitance by light scabbing or grit-blasting. The effectiveness of decontamination should then be assessed by a pull-off test.

Substrate priming

The substrate should be thoroughly soaked with clean water and any excess removed prior to commencement. A slurry primer should be prepared consisting of 1 volume Expanbond* SBR to 1 volume clean water to 3 volumes fresh cement. To obtain a smooth consistency, the cement should be blended slowly into the premixed liquid. The slurry primer should be stirred frequently during use to offset settlement.

The slurry primer should be scrubbed well into the surface of the substrate, being careful to avoid ponding. The repair mortar, topping or render must be applied on to the wet slurry primer. If the slurry primer dries before application of the mortar, it must be removed and the area re-primed before continuing.

Preparation of reinforcement (repairs only)

Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Grit-blasting is recommended for this process.

Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after grit-blasting to remove corrosion products from pits and imperfections within its surface.

Reinforcing steel priming

Apply one full coat of Expanprime* Zincrich to any exposed steel reinforcement and allow to dry before continuing. If any doubt exists about having achieved an unbroken coating, a second application should be made and, again, allowed to dry before continuing.

Mix designs

A wide range of mix designs is achievable using Expanbond* SBR.

Mixing

Care should be taken to ensure that Expanbond* SBR mortars are thoroughly mixed. A forced-action mixer is essential for large volume applications. Mixing in a suitably sized drum using an approved spiral paddle in a slow speed (400/500 rpm) heavy-duty drill is acceptable for minor areas.

Weigh the cement, sand and where required, aggregate into the mixer and dry blend together for one minute. With the machine in operation, add the pre-mixed Expanbond* SBR and clean water. Continue mixing for 3 minutes to ensure complete dispersal into the sand and cement. Make any small adjustment to the quantity of clean water but do not significantly exceed the literage shown above, additional water should be kept to a minimum.

Continue mixing up to a maximum of 5 minutes until a smooth and full homogeneous consistency is achieved with the required workability and application properties. It is critical that allowance is made for the moisture content of the sand and aggregate, particularly where stored on site.

Application

For application to all surfaces, Expanbond* SBR mortars, toppings and renders must be well-compacted on to the a thin layer of the mortar into the slurry primer and then build the mortar on to this layer. Exposed steel reinforcement should be completely encapsulated by the mortar.

Expanbond* SBR mortars can be applied at a minimum thickness of 6 mm and up to 40 mm thickness, dependent on the location and configuration of the repair zone. Refer to the recommended thicknesses shown in the Mix design section above.

If the recommended thickness is exceeded and sagging occurs, the affected section must be completely removed and reapplied in accordance with the procedure described above. The use of formwork may facilitate achieving the required build. If formwork is used, it should have properly sealed faces to ensure that no water is absorbed from the repair material.

Where thicker sections (up to a total thickness of 40 mm) are to be built up by hand or trowel application, the surface of the intermediate layers should be scratch-keyed and cured with Expanbond* AR. Application of the slurry primer and a further application of Expanbond* SBR mortar may proceed as soon as this layer has set.



CONSTRUCTION CHEMISTRY

Finishing

Expanbond* SBR mortars can be finished with a steel, plastic or wood float, or by a damp sponge technique, to achieve the desired surface texture. The completed surface should not be overworked.

Low temperature working

In cold conditions down to 15°C, the use of warm water (up to 30°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should then be adopted.

High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade and cool water used for mixing.

Curing

Expanbond* SBR mortars, toppings and renders are cement-based. In common with all cementitious materials, they must be cured immediately after finishing in accordance with good concrete practice.

The use of Expanbond* AR or Expancure RB90, sprayed on to the surface of the finished mortar in a continuous film, is recommended. In harsh drying conditions, supplementary curing with polythene sheeting must be used.

Over-coating with protective decorative finishes

Expanbond* SBR mortar repairs are extremely durable and will provide excellent protection to the embedded steel reinforcement within the repaired locations.

The surrounding parts of the structure will generally benefit from the application of a barrier/decorative coating to limit the advance of chlorides and carbon dioxide, thus brining them up to the same protective standard as the repair itself.

Expanchem Fospak recommend the use of the Expancote* range of protective, anti-carbonation coatings. These products provide a decorative and uniform appearance as well as protecting areas of the structure which might otherwise be at risk from the environment.

Expancote* products may be applied over the repair area without prior removal of the Expanbond* AR curing membrane. Expancure* RB90 curing membrane must be removed prior to the application of Expancote* products. This is best achieved by light grit or sand-blasting.

Cleaning

Expanbond* SBR and Expanbond* AR should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Equipment used with Expanprime* Zincrich and Expancure* RB90 should be cleaned using Expanchem Solvent 102.

Limitations

Expanbond* SBR mortars, toppings and renders should not be applied when the temperature is below 5°C and falling.

Expanbond* SBR mortars should not be exposed to moving water during application. Exposure heavy rainfall prior to the final set may result in surface scour.

If any doubts arise concerning temperature or substrate conditions, consult the local Expanchem Fospak office. Technical support Expanchem Fospak offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an Auto CAD facility and dedicated specification assistance in locations all over the world.

Estimating

Supply

Expanbond* SBR	: 5, 30 and 210 liter drums
Expanprime Zincrich	: 1 liter cans
Expanbond AR	: 1 & 5 Liter cans
Expancure RB90	: 30 and 210 liter drums
Expanchem Solvent 102	: 5 liter cans

Coverage

Expanbond* SBR	: Refer to mix designs
Expanbond* SBR	: Approx. 2 to 3m ² /liter (as slurry primer)

Note: The actual usage of Expanbond* SBR will depend on the mix design used. The coverage figures for liquid products including the Expanbond* SBR slurry primer are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.



CONSTRUCTION CHEMISTRY

Storage

Shelf life

All products have a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs.

Storage conditions

Store in dry conditions in original packing. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced. Expanbond* SBR and Expanbond* AR. Should be protected from frost.

Precautions

Health and safety

Cementitious mortars and slurries modified with Expanbond* SBR contain cement powders which, when mixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes. Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment. The use of barrier cream provides additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.

Expanprime* Zincrich, Expanbond* products, Expancure* RB90 and Expanchem Solvent 102 should not come in contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provide additional skin protection.

In case of skin contact with Expanprime* Zincrich and Expancure* RB90, remove immediately with resin removing cream followed by washing with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.

Fire

Expanbond* SBR and Expanbond* AR are non-flammable. Expanprime* Zincrich, and Expanchem Solvent 102 are flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO₂ or foam do not use water jet.

Flash points

Expanprime Zincrich	:	16°C
----------------------------	---	------

Expanchem Solvent 102	:	33°C
------------------------------	---	------

For further information, refer to the Product Material Safety Data Sheet.



CONSTRUCTION CHEMISTRY

* Denotes the trademark registered.

REGIONAL SALES OFFICES IN PAKISTAN:

Fospak (Pvt) Ltd.

Head Office

702, Business Avenue,
Block-6, PECHS., Shakra-e-Faisal,
Karachi, Pakistan.

Tel # +92-21-34528477, 34529859

Fax # +92-21-34522436

Email : info.khi@fospak.com.pk

Lahore Sales Office

2nd Floor Sarwar Shaheed Plaza,
Cavalry Ground,
Main Boulevard, Lahore Cantt,
Lahore, Pakistan.

Tel # +92-42-36675773

Fax # +92-42-36675838

Email : info.lhr@fospak.com.pk

Rawalpindi Sales Office

1st Floor,
Al-Harmain Plaza,
Main Murree Road,
Rawalpindi, Pakistan.

Tel # +92-51-9290592

Fax # +92-51-9290590

Email : info.isb@fospak.com.pk

Important note

Expanchem Fospak products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Expanchem Fospak endeavours to ensure that the technical information on this data sheet is correct at the time of printing, it is the customer's responsibility to satisfy himself, by checking with the company that this information is still current at the time of use, that the product is suitable for the intended application, and that the actual conditions of use are in accordance with those recommended. Because Expanchem Fospak has no control over the conditions of use of its products, all recommendations or suggestions regarding the use of these products are made without guarantee.

www.fospak.com