

Expancure* AB

Acrylic based curing compound

Uses

As a spray applied membrane for exterior or interior application on renders or concrete surfaces. Particularly suitable for situations where after trades, such as paints or renders are to be applied.

Advantages

- Improved curing of concrete enhances hydration process and provides a more durable concrete.
- Control of moisture loss improves surface quality, reducing permeability, minimizing surface cracking and shrinkage.
- Compatible with many after-trade applications.
- Water based, therefore, non-flammable.
- Spray application reduces labor costs, therefore eliminates the need for alternative curing systems.

Standards compliance

Expancure* AB gives 75% or greater curing efficiency when tested to BS 7542 and complies with BS 8110 Part 1, clause 6.6.3(c), ASTM C309 and AASHTO M148 as Type 1D.

Description

Expancure* AB water based concrete curing compound is based on acrylic polymer. It is supplied as a white emulsion which forms a clear film on drying. When first applied to a fresh cementitious surface the emulsion breaks to form a continuous, non-penetrating coating. This dries to form a continuous clear film which provides a barrier to moisture loss, ensuring more efficient cement hydration, improved durability and reduced shrinkage.

Expancure* AB is also available in a white pigmented version; It contains a white pigment based on titanium dioxide to meet specifications requiring such pigmentation for reduction of solar temperature gain.

Instructions for use

Application

Expancure* AB white should be stirred before use to ensure even dispersal of the pigment.

Expancure* AB should be spray applied to the surface of fresh concrete. Application should begin as soon as the concrete is free from surface water. Do not apply if bleed water is forming, or is present on the concrete surface.

The spray nozzle should be held approximately 450 mm from the concrete surface and passed back and forth to ensure complete coverage. The fugitive white color during application provides a guide to the area covered. Pump pressure should be maintained to give an even, fine spray.

After spraying, no further application of water or other material is necessary to ensure continued curing. The concrete surface should not be disturbed until it has sufficient strength to bear surface loads. The applied film should not be trafficked until it is fully dry, care should also be taken to ensure that the film is not subsequently broken.


Expancure* AB may be applied to the surface of newly hardened concrete immediately after de-moulding, in such cases the concrete surface must be damp and not dry.

Equipment

Spray equipment such as motorized sprayers which produce a fine mist without damaging the emulsion may be used for Expancure* AB. The suitability of equipment should be assessed by an application trial.

Equipment cleaning

Spray equipment should be cleaned immediately after use by flushing through with water. If spray nozzles become blocked, these may be easily cleared with white spirit.



Over-coating and removal

It is not necessary to remove Expancure* AB prior to the application of a coating, plastering, rendering, tiles fixing etc.

Limitations

Expancure* AB should not be continuously re-circulated in high shear pumps in concrete train or similar applications, as this may cause a breakdown of the emulsion before spraying. If continuous recirculation is necessary, the sprayer should be fitted with a low shear diaphragm pump.

Minimum application temperature 5°C.

Technical support

Fospak provides a technical advisory service for on-site assistance and advice on admixture selection, evaluation trials and dispensing equipment. Technical data and guidance can be provided for admixtures and other products for use with fresh and hardened concrete

Estimating

Supply

Expancure* AB :	30 & 210 Ltr. Drum
-----------------	--------------------

Coverage

Expancure* AB :	4.00 – 6.00 m ² / Ltr.
-----------------	-----------------------------------

Storage

Expancure* AB has a minimum shelf life of 12 months, provided the temperature is kept within the range of 4°C to 35°C.

Freezing and prolonged exposure to heat or direct sunlight should be avoided. Should the temperature of the product fall outside this range then the Fospak Technical Service Department should be contacted for advice. Containers should be kept sealed and airtight to prevent loss of moisture by evaporation.

Precautions

Health and safety

Expancure* AB does not fall into the hazard classifications of current regulations (see notes 1 and 2 below). However, it should not be swallowed or allowed to come into contact with skin and eyes either in bulk or spray form. Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - **do not** induce vomiting.

For further information consult the Material Safety Data Sheet available for this product.

Fire

Expancure* AB is water based and non-flammable.

* Denotes the trademark registered

REGIONAL SALES OFFICES IN PAKISTAN:

Fospak (Pvt) Ltd.

Head Office

702, Business Avenue,
Block-6, PECHS.
Shahra-e-Faisal,
Karachi, Pakistan
Tel # +92-21-34528477, 34529859
Fax # +92-21-34522436
Email info.khi@fospak.com.pk

Lahore Sales Office

2nd Floor Sarwar Shaheed Plaza,
Cavalry Ground,
Main Boulevard,
Lahore Cantt, Lahore.
Tel # +92-42-36675773
Fax # +92-42-36675838
Email info.lhr@fospak.com.pk

Rawalpindi Sales Office

1st Floor, Al-Harmain Plaza,
Main Murree Road,
Rawalpindi
Tel # +92-51-9290592
Fax # +92-51-9290590
Email info.isb@fospak.com.pk

Important note

Fospak products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fospak endeavours to ensure that the technical information on this data sheet is correct at the time of printing, it is the customer's responsibility to satisfy himself, by checking with the company that this information is still current at the time of use, that the product is suitable for the intended application, and that the actual conditions of use are in accordance with those recommended. Because Fospak has no control over the conditions of use of its products, all recommendations or suggestions regarding the use of these products are made without guarantee.