

Expangrout* PU300S

Single component, fast setting polyurethane injection resin grout

Uses

For injecting into cracks in concrete / masonry / rock / hard soil, either wet or dry to form an elastic seal, and provides an effective system for cracks sealing in wet conditions, and suitable for the injection in defective or honeycombed concrete, concrete joints, cavities in rock or brick construction, pipe intrusions, tunnels and dam, sewers, manholes, waste water tanks etc.

Advantages

- Single component, low viscosity allows penetration into the finest cracks
- Good adhesion to dry or moist substrate
- Flexible to withstand differential movement
- Stand high hydrostatic pressures
- Can be inject with 1-C pumps
- Cures to an impermeable mass
- Odor less suitable for grouting in confined area

Description

Expangrout PU300S is a single component injection resin based on polyurethane, which is use for stopping water ingress, for stopping flowing water, Expangrout EP300S can be use independently or with Expangrout EP350C catalyst/accelerator to reduce the setting time.

Expangrout PU300S reacts with the water/moisture present in the injection area and form a foam formation, with the addition of up to 10% Expangrout PU350C catalyst/accelerator to the Expangrout PU300S polyurethane resin, will reduce the final setting time of grout, and suitable for use in high water pressure.

Expangrout PU300S is extremely well suited for filling of large cavernous spaces and cracks in stone or concrete structures as well as for cutting off running water. Due to the low viscosity of the material, Expangrout PU300S offers superior penetration in hairline crack injection.

Properties

The following properties were obtained at a temperature of 20 °C unless otherwise specified.

Component	PU300S	PU350C
Consistency	Liquid	Liquid
Appearance	Dark brown	Light yellow
Viscosity (@ 20 °C)	: Approx 870 mPas	
Odor	: Odorless	Slight odor
Specific gravity	: 1.13 g/cm ³	1.01 g/cm ³

Additions of Expangrout PU350C catalyst/accelerate reduce the pot life and setting time of grout, the foaming time details are given below.

Reaction Data

Component	PU300S	With PU350C Catalyst	
		5%	10%
Starting time (Foaming Begin) min:sec	0:30 ± 0:05	0:25 ± 0:05	0:15 ± 0:05
Rise time (Foaming) min:sec	2:20 ± 0:05	1:45 ± 0:05	1:00 ± 0:05
Bulk density	39 kg/m ³	25 kg/m ³	22 kg/m ³

Instructions for use

Expangrout PU300S can be applied using either injection packers fixed into holes drilled directly into the crack or drilled diagonally from concrete adjacent to the crack or by the fixing of injection nipples bonded to the surface using Expanmortar EPFC(B).

Preparation

Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae.

The surface should preferably be prepared using high pressure water jetting or light abrasive blasting, followed by thorough washing to remove dust and remaining particles. Dirt alone may be removed with wire brushes or similar mechanical means.

Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should be assessed by a pull-off test.

Blow the cracks and treated surface with oil free air to ensure complete removal of all dust and loose particles.

In the presence of high pressure running water the flow must be stopped using Expangrout PU300S with 10% Expangrout PU350C catalyst/accelerator which produce rapid setting water-stopping foam. When the water is stopped the cracks are re-injected with Expangrout PU300S.

All cracks must be sealed, and injection packers or nipples located in place before Expangrout PU300S is injected.

Fixing injection packers

The injection packers shall be inserted into pre-drilled holes at intervals along the length of each crack. The distance between each packer will depend upon the width and depth of the crack. Spacing shall be close enough to ensure that the resin will penetrate along the crack to the next point of injection. This will normally be between 200 mm to 500 mm.

The surface of the cracks between the packers shall be sealed with Expanmortar EPFC(B), 30 to 40mm wide and 2 to 3 mm thick. Both sides of any cracks which go all the way through a wall or slab shall be sealed in this way. In the case of a wall or slab cracked all the way through, packers shall be located on both sides with those at the back placed at midway points between those at the front.

The Expanmortar EPFC(B) shall be allowed to cure for 6 - 8 hours at 35°C. At low ambient temperatures (5°C to 12°C) the curing time will be extended and the applicator shall ensure that the surface sealant has adequately cured prior to continuing.

The use of Expanmortar EPFC(B) for the sealing of crack surface between the packers is optional, cured Expangrout EP300S which is flow-out from crack surface in form of foam shall be cut-off with sharp knife to even the surface.

One end of the injection hose shall be attached to the lowest packer on vertical cracks or to either end of the horizontal cracks. Each crack shall be treated in a single, continuous operation. Sufficient material shall, therefore, be made ready prior to the commencement of the work.

Expangrout PU300S application

Expangrout PU300S should be used with standard injection equipment having closed containers. The injection pressure should be at least 0.4N/mm² (4 bar).

Only mix sufficient resin that can be used within the pot life of the material.

After grouting remove the packers and fill holes or voids with Expanmortar EPFC(B) and allow to cure. The Expanmortar EPFC(B) can be ground off or softened with a blow lamp and peeled off. Do not allow to burn.

Cleaning

Expangrout PU300S and Expanmortar EPFC(B) should be removed from tools, equipment and mixers with Fospak Solvent 102* immediately after use. Hardened material can only be removed mechanically.

Limitations

Expangrout PU300S is only to be used in dry or damp concrete/masonry/stone/rock/hard soil etc., if contact with running water is expected the associate product Expangrout PU300S with Expangrout PU350C catalyst/accelerator should be considered. If any doubts arise concerning temperature, application or substrate conditions, consult the local Fospak office.

Technical support

Fospak offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Estimating

Supply

Expangrout PU300S	:	22 kg. can
Expangrout PU350C Catalyst	:	2.20 kg can
Expanmortar EPFC(B)	:	1 kg. pack
Fospak Solvent 102	:	5 liter can

Storage

Shelf life

All products have a shelf life of 6 months at 20 °C if kept in a dry store in the original, unopened containers.

Storage conditions

Store in dry conditions in the original, unopened containers. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced to 2 to 3 months.

Precautions

Health and safety

Expangrout PU300S may cause sensitization by inhalation. During use avoid contact with skin and eyes. Ensure adequate ventilation and avoid inhalation of vapors.

Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye/face protection. If working in confined areas, suitable respiratory protective equipment must be used.

The use of barrier creams provides additional skin protection. Should accidental skin contact occur, remove immediately with a resin removing cream followed by soap and water. Do **not** use solvent.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice.

If swallowed seek medical attention immediately - do not induce vomiting. Use only in well ventilated areas. In cases of insufficient ventilation wear suitable respiratory protective clothing.

Fire

Expangrout PU300S, PU350C and Expanmortar EPFC(B) are flammable, avoid to contact with direct flame.

Fospak Solvent 102 is highly flammable. Keep away from sources of ignition. No smoking. In the event of fire extinguish with CO₂ or foam. Do not use a water jet.

Flash points

Fospak Solvent 102	:	33 °C
--------------------	---	-------

For further information, refer to the Product Material Safety Data Sheet.

Additional Information

Fospak manufactures a wide range of complementary products which include:

- waterproofing membranes & waterstop
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialized flooring materials

Fospak additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Systematic approach to concrete repair features the following:

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fospak office - as below.

*** Denotes the trademark registered**

REGIONAL SALES OFFICES IN PAKISTAN:

Fospak (Pvt) Ltd.

Head Office

702, Business Avenue,
Block-6, PECHS.
Shahra-e-Faisal,
Karachi, Pakistan

Tel # +92-21-34528477, 34529859

Fax # +92-21-34522436

Email info.khi@fospak.com.pk

Lahore Sales Office

2nd Floor Sarwar Shaheed Plaza,
Cavalry Ground,
Main Boulevard,
Lahore Cantt, Lahore.

Tel # +92-42-36675773

Fax # +92-42-36675838

Email info.lhr@fospak.com.pk

Rawalpindi Sales Office

1st Floor, Al-Harmin Plaza,
Main Murree Road,
Rawalpindi

Tel # +92-51-9290592

Fax # +92-51-9290590

Email info.isb@fospak.com.pk