



CONSTRUCTION CHEMISTRY

Expanplast* SP423C**

Workability retention superplasticiser, and set accelerator

Uses

- Gives increased working life to fresh concrete.
- Increases workability without extra water, reducing placing time and costs.
- Improves cohesion, minimising segregation and improving surface finish.
- Aids pumping by improving cohesion and reducing workability loss.
- Allows a reduction in water : cement ratio, enhancing durability by producing low permeability concrete with reduced shrinkage cracking potential.
- Chloride free, safe for use in prestressed and reinforced concrete.
- Can be used with concrete containing microsilica and other cement replacements.

Standards compliance

Expanplast* SP423C** conforms with BS 5075 Part 3, and ASTM C494 as Type E & F

Description

Expanplast* SP423C** is a chloride free workability retention admixture based on selected synthetic polymers, it is supplied as brown solution which instantly disperses in water.

Expanplast* SP423C** disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively. The initial hydration of the cement is also delayed; the improved dispersion of cement particles enhances the efficiency of hydration. At higher dosage levels retardation of setting will be obtained.

Technical support

Epanchem Fospak provides a technical advisory service for on-site assistance and advice on admixture selection, evaluation trials and dispensing equipment.

Dosage

The optimum dosage of Expanplast* SP423C** to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use.

The normal dosage range is from 0.60 to 1.50 liters/100 kg of cementitious material, including PFA, GGBFS and microsilica

Use at other dosages

Dosages outside the typical ranges quoted above may be used to meet particular mix requirements. Contact Epanchem Fospak for advice in these cases.

Effects of overdosing

An overdose of double the intended amount of Expanplast* SP423C** will result in a significant increase in retardation as compared to that normally obtained at the intended dosage.

Retardation

The level of retardation obtained may be varied by altering the dosage of Expanplast* SP423C** used, which will also alter the level of water reduction obtained. Retardation is also affected by factors other than the admixture, depending on the mix details and conditions involved. Major factors include the following:

a) Cement replacement materials and SRC cements will usually give greater levels of retardation than concrete mixes made with ordinary Portland cement at the same admixture dosage.

b) High temperatures will require increased dosages to obtain the same change in stiffening time compared to a control mix.

c) Changes in cement content, source or chemistry may lead to variations in the retardation obtained. The amount of tri-calcium aluminate in the cement has been identified as being one of the main contributory factors in this respect, with a lower level leading to greater retardation.

d) The use of a combination of admixtures in the same concrete mix may alter the setting time. Trials should always be conducted to determine such setting times.

Properties

Appearance : Brown liquid

Specific gravity : Typically 1.158 ± 0.005 at 20°C

Air entrainment : Typically less than 2% additional air is entrained at normal dosages.



Instructions for use

Mix design

The addition of the admixture will allow water reduction from the mix whilst maintaining workability. After initial trials, minor modifications to the overall mix design may be made to optimize performance.

Where the primary intention is to provide high workability concrete, the mix design should be suitable for use as a pump mix. Advice on mix design for flowing concrete is available from Fospak.

Compatibility

Expanplast* SP423C** is compatible with other Epanchem Fospak admixtures in the same concrete mix. All admixtures should be added to the concrete separately and must not be mixed together prior to addition. The trial mixes should assess the resultant properties of concrete containing more than one admixture.

Expanplast* SP423C** is suitable for use with all types of cements OPC, SRC and cement replacement materials such as PFA, GGBFS, and silica fume.

The use of a combination of admixtures in the same concrete mix and or cement replacements may alter the setting time. Trials should always be conducted to determine such setting times.

Dispensing

The correct quantity of Expanplast* SP423C** should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Contact Epanchem Fospak for advice regarding suitable equipment and its installation.

Estimating - packaging

Expanplast* SP423C** is available in 210 liter drums and bulk supply for large volume users.

Storage

Expanplast* SP423C** has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then contact your local Epanchem Fospak office for advice.

Freezing point: Approximately -4°C

Precautions

Health and safety

Expanplast* SP423C** does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately do not induce vomiting.

For further information consult the Material Safety Data Sheet available for this product.

Fire

Expanplast* SP423C** is water based and non-flammable.

Cleaning and disposal

Spillages of Expanplast* SP423C** should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.



**** Especially modified for New Khanki Barrage Project, with control retardation to meet the specific project requirements, except the control retardation other properties are same as mentioned in Expanplast* SP423C** technical data sheet.**

*** Denotes the trademark registered.**

REGIONAL SALES OFFICES IN PAKISTAN:

Fospak (Pvt) Ltd.

Head Office

702, Business Avenue,
Block-6, PECHS., Shahr-e-Faisal,
Karachi, Pakistan.

Tel # +92-21-34528477, 34529859

Fax # +92-21-34522436

Email : info.khi@fospak.com.pk

Lahore Sales Office

2nd Floor Sarwar Shaheed Plaza,
Cavalry Ground,
Main Boulevard, Lahore Cantt,
Lahore, Pakistan.

Tel # +92-42-36675773

Fax # +92-42-36675838

Email : info.lhr@fospak.com.pk

Rawalpindi Sales Office

1st Floor,
Al-Harmin Plaza,
Main Murree Road,
Rawalpindi, Pakistan.

Tel # +92-51-39290592

Fax # +92-51-39290590

Email : info.isb@fospak.com.pk

Important note

Expanchem Fospak products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Expanchem Fospak endeavours to ensure that the technical information on this data sheet is correct at the time of printing, it is the customer's responsibility to satisfy himself, by checking with the company that this information is still current at the time of use, that the product is suitable for the intended application, and that the actual conditions of use are in accordance with those recommended. Because Expanchem Fospak has no control over the conditions of use of its products, all recommendations or suggestions regarding the use of these products are made without guarantee.

www.fospak.com