

Expanproof* GP2000

Polyester reinforced self-adhesive bituminous waterproofing membrane

Uses

To provide a continuously bonded waterproof membrane for building and civil engineering structures, below ground structures, subways, water retaining and water excluding structures, tunnels etc.

Advantages

- 2 mm thick (Nominal).
- Cold applied.
- Fast application.
- Uniform thickness of polymer bitumen membrane.
- Good adhesion to primed concrete substrates.
- Produces a continuous waterproof membrane system.

Description

Expanproof GP2000 is a cold applied self-adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with a dimensionally stable non woven polyester rot-proof fabric, bonded on to an outer surface of cross laminated polyethylene film. The polymer bitumen adhesive layer is protected on the underside by a silicone release paper which is removed just prior to the application of Expanproof GP2000 to the primed substrate.

The applied membrane is then immediately protected from UV light and from mechanical damage during subsequent back filling by the application of Protection Board, or a sand/cement screed.

Specification

The waterproofing membrane shall be a 2 mm thick self adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with non-woven polyester rot-proof fabric, bonded on to an outer surface of polyethylene film.

Technical support

Fospak offers a comprehensive technical support service to specifiers, end users and contractors.

Properties

| | |
|---|---------------------------------------|
| Tensile strength (DIN EN 12311-1) | : Long 300 N/5 cm Trans 250 N/5 cm |
| Elongation (DIN EN 12311-1) | : Long 30% Trans 35% |
| Elongation of compound (ASTM D412) | : >2000% |
| Adhesion to prime concrete (ASTM D1000) | : 1.80 N/mm ² |
| Adhesion to self (ASTM D1000) | : 2.20 N/mm ² |
| Puncture Resistance (ASTM E154:1993) | : > 400 N |
| Chemical resistance pH (ASTM D543) | : 2.50 – 11.50 |
| Hydrostatic pressure @ 5 bar (50 m) (BSEN 12390 Part 8) | : No leakage |
| Crack bridging (ASTM C836:1995) | : > 1 mm |
| Tear resistance (ASTM D5147) | : Long 300 N Trans 200 N |

Instructions for use

Surface preparation


Concrete surfaces should be float finished and free from cavities and projecting nibs. All surfaces shall be dry and free from frost, surface laitance and contamination.

Priming

Expanproof Primer must be applied to the substrate and allowed to dry until it is tack free, prior to the application of the membrane. All surfaces must be re-primed if left for more than 24 hours prior to the application of Expanproof GP2000.

Application

Smooth transition should be made at wall/floor slab junctions using a sand/cement mortar and internal and external corners at walls and up stands pre-protected with Expanproof Corner Pieces prior to the application of the membrane.



The membrane should be applied to the substrate having first removed the siliconized release paper, pressing the polyethylene film firmly ensuring that the adhesive bitumen compound bonds continuously to the substrate with no air pockets.

Allow at least a 75mm edge and a 150mm end lap. All laps should be rolled firmly to achieve a good seal. End laps should be staggered.

On vertical or inclined surfaces, the membrane shall be laid from the lowest level upwards.

The membrane should be protected immediately after application in accordance with BS 8102:1990 by using Protection Board, or as appropriate with a sand/cement screed.

Limitations

Application temperature range: 5 °C – 50 °C.

For application below 15 °C it may be necessary to slightly warm the back of the membrane to achieve an immediate bond. In cold conditions the membrane should be stored at temperatures above 20°C prior to application to facilitate ease of application and immediate bond to the substrate.

Estimating / Supply

| | |
|-------------------|-----------------------------|
| Expanproof GP2000 | : 10 mt long x 1m wide roll |
| Expanproof Primer | : 20 kg. drums |

Coverage

| | |
|-------------------|----------------------------------|
| Expanproof Primer | : 3 – 6 m ² per liter |
|-------------------|----------------------------------|

Storage

All products have a shelf life of 12 months if stored in a cool, dry store, away from sources of heat, in the original unopened packing. It should be stored horizontally, not more than one pallet high.

Precautions

Health and safety

There are no health hazards associated with the use of Expanproof GP2000 and Protection Board.

If Expanproof Primer is swallowed, **do not** induce vomiting - drink a glass of water. If contact with eyes occurs, flood with copious amounts of clean water for at least 15 minutes and seek medical advice. If on the skin, remove any contaminated clothing and wash skin thoroughly.

For further information, please consult Material Safety Data Sheets for the above products.

Fire

Expanproof GP2000 and Protection Board are flammable. Keep away from sources of ignition. Do not smoke in the presence of these products. Expanproof Primer contains volatile, flammable solvents. Use only in ventilated areas, well away from any ignition source.

Flash points

| | | |
|-------------------|---|---------|
| Expanproof GP2000 | : | > 65 °C |
| Expanproof Primer | : | > 38 °C |

* Denotes the trademark registered

REGIONAL SALES OFFICES IN PAKISTAN:

Fospak (Pvt) Ltd.

Head Office

702, Business Avenue,
Block-6, PECHS.
Shahra-e-Faisal,
Karachi, Pakistan

Tel # +92-21-34528477, 34529859

Fax # +92-21-34522436

Email info.khi@fospak.com.pk

Lahore Sales Office

2nd Floor Sarwar Shaheed Plaza,
Cavalry Ground,
Main Boulevard,
Lahore Cantt, Lahore.

Tel # +92-42-36675773

Fax # +92-42-36675838

Email info.lhr@fospak.com.pk

Rawalpindi Sales Office

1st Floor, Al-Harmain Plaza,
Main Murree Road,
Rawalpindi

Tel # +92-51-9290592

Fax # +92-51-9290590

Email info.isb@fospak.com.pk