

Expanplast* SP561R**

High performance, high workability slump retaining water reducing superplasticiser, with additional retardation

Uses

- To improve the effectiveness of the water content of a concrete mix.
- At higher dosages, provides cost effective means of reducing concrete permeability and thereby reducing water penetration.
- Extra retardation minimize the risk of cold/construction joint in mass concrete, and reduce the peak exotherm.
- Suitable to use in mass concrete, provides excellent workability retention.

Advantages

- Allows specified strength grades to be met at reduced cement content or increased workability
- Water reduction significantly improves compressive strength at all ages and enhances durability through the production of low permeability concrete.
- Minimizes the risk of segregation, bleeding and assists in the production of a dense, close textured surface, improving durability.
- Chloride free, safe for use in pre-stressed and reinforced concrete.
- Allows workability to be increased without adding extra water, suitable for high workability concrete.

Standards compliance

Expanplast* SP561R** conforms with BS 5075 Part 1, ASTM C494 as Type B, D, & G

Description

Expanplast* SP561R** is a chloride free and water reducing admixture based on specially selected and blended organic polymers materials. It is supplied as a brown solution which instantly disperses in water.

Expanplast* SP561R** disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively and improve the consistency of concrete. This produces higher levels of workability for the same water content, allowing benefits such as water reduction, slump retention, retardation, and increased strengths by reducing water cement ratio.

Technical support

Fospak provides a technical advisory service for on-site assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

Dosage

The optimum dosage of Expanplast* SP561R** to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. The normal dosage range is between 0.50 to 2.00 liters/100 kg of cementitious material.

Use at other dosages

Dosages outside the normal range quoted above can be used to meet particular mix requirements. Contact Fospak for advice in these cases.

Effects of overdosing

An overdose of double the intended amount of Expanplast* SP561R** will result in a significant increase in retardation as compared to that normally obtained at the intended dosage. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased. The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used.

Over dosage may also cause increased air entrainment, which will tend to reduce strength. The degree of this effect will depend on the particular mix design and overdose level.

Properties

Appearance :	Brown liquid
Specific gravity (BSEN 934-2) :	1.175 - 1.185 @ 20°C

Instructions for use

Compatibility

Expanplast* SP561R** is compatible with other Fospak admixtures used in the same concrete mix. All admixtures should be added to the concrete separately and must not be premixed together prior to addition. The performance of concrete containing more than one admixture should be assessed by trial mixes.

Expanplast* SP561R** is suitable for use with all types of Portland cements and cement replacement materials such as PFA, GGBFS, SRC and microsilica. The use of a combination of admixtures in the same concrete mix and or cement replacements may alter the setting time. Trials should always be conducted to determine such setting times.

Dispensing

The correct quantity of Expanplast* SP561R** should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Contact Fospak for advice regarding suitable equipment and its installation.

Estimating - packaging

Expanplast* SP561R** is available in 210 liter drums and bulk supply. For larger users, storage tanks can be supplied.

Storage

Expanplast* SP561R** has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then contact Fospak for advice.

Freezing point: Approximately - 3°C

Precautions

Health and safety

Expanplast* SP561R** does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - **do not induce vomiting**.

For further information consult the Material Safety Data Sheet available for this product.

Fire

Expanplast* SP561R** is water based and non-flammable.

Cleaning and disposal

Spillages of Expanplast* SP561R** should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

**** Especially modified for Sapphire 50MW Wind Power Project, with additional retardation to meet the specific project requirements, except the additional retardation other properties are same as mentioned in Expanplast* SP561 technical data sheet.**

* Denotes the trademark registered

REGIONAL SALES OFFICES IN PAKISTAN:

Karachi Head Office

702, Business Avenue,
Block-6, PECHS.
Shahra-e-Faisal,
Karachi, Pakistan
Tel # +92-21-34528477, 34529859
Fax # +92-21-34522436
Email info.khi@fospak.com.pk

Lahore, Sales Office

2nd Floor Sarwar Shaheed Plaza,
Cavalry Ground,
Main Boulevard, Lahore Cantt.
Lahore, Pakistan.
Tel # +92-42-36675773
Fax # +92-42-36675838
Email info.lhr@fospak.com.pk

Islamabad, Sales Office

1st Floor, Al-Harmain Plaza,
Main Murree Road,
Rawalpindi
Pakistan
Tel # +92-51-4575746
Fax # +92-51-9290590
Email info.isb@fospak.com.pk

www.fospak.com